

4831 S. Whipple Avenue Chicago IL 60632 Phone: 773.523.3100 Fax: 773.523.4008 www.accu-labs.com

A2LA Accredited ISO/IEC 17025:2005 Certificate # 2558.01

$903\,$ metal conditioner & aluminum brightener

ACCU-LABS 903 has been developed to economically clean and prepare aluminum surfaces prior to painting. ACCU-LABS 903 is also used by the transportation industry for cleaning aluminum bodied vehicles. ACCU-LABS 903 is economically attractive because of its ability to remove a wide variety of soils as a soak cleaner. 903 may also be used to remove brazing and soldering fluxes from steel, brass, stainless steel, etc.

OPERATING GUIDELINES:

Concentration: 20% (by volume with water) - 100%

Temperature: Room temperature - 180°F

Dwell Time: 30 seconds – 5 minutes (applications vary)

Tank: Stainless Steel, PE, PP, PVC lined tank

ANALYTICAL CONTROL: Using a standard hydrometer maintain specific gravity at 1.35 by adding 903 Metal Conditioner when specific gravity falls below 1.35.

HANDLING: Always wear eye protection and personal protective gear when handling or working with this product, read MSDS before using.

NOTICE OF NON WARRANTY

The information contained in this bulletin is, to our best knowledge, true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. ACCU-LABS, INC. disclaims any liability incurred in connection with the use of these data or suggestions.