

ACCU-LABS INC.

4831 S. Whipple Avenue
Chicago IL 60632
Phone: 773.523.3100 Fax: 773.523.4008
www.accu-labs.com

A2LA Accredited ISO/IEC 17025:2005 Certificate # 2558.01

DX-14 ALUMINUM DESMUT *Liquid Deoxidizer - Desmut for Aluminum*

Introduction

Accu-Labs DX-14 is a chrome-free liquid Desmut/deoxidizer for all wrought and extruded aluminum alloys. **ACCU-LABS DX-14** is formulated to achieve a clean, white, aluminum surface free of silicon and alloying metals. **ACCU-LABS DX-14** is especially effective for troublesome high-silicon 6000 series alloys, producing maximum quality for your anodized or chromated work. **ACCU-LABS DX-14** works well with 628-CC non-chromate conversion coating for aluminum.

Features and benefits

Liquid product	Easy to mix and measure
Versatile	Works on all wrought and extrusion alloys
Economical	Long solution life
Non-chromated formula	Safer for employees and environment

Operating guidelines for ACCU-LABS DX-14 Desmut

Concentration	5-25% by volume
Immersion time	30 seconds-5 minutes
Temperature	65-105 ⁰ F
Agitation	Recommended

Make-up and maintenance of ACCU-LABS DX-14 Desmut solutions

Properly maintaining your **ACCU-LABS DX-14 Desmut** solution will result in excellent production rates and maximum solution life.

- 1) Clean and rinse all tanks and equipment before making up working solution. All construction should be of suitable strength polypropylene or polyethylene, reinforced as necessary. (Steel, protected by a drop-in liner, is acceptable; however, tears in the liner will allow escape of solution that could corrode the steel.)
- 2) Fill tank $\frac{3}{4}$ full with water (tap water is generally suitable). Add the required amount of **ACCU-LABS DX-14 Desmut** based upon your typical usage. Mix thoroughly.
- 3) Fill tank to working volume. If solution is colder than suggested, live steam or corrosion-resistant immersion heaters may be used to bring temperature into working range. Solution is now ready to use.
- 4) Use only the amount of **ACCU-LABS DX-14 Desmut** required for your type of work. Excess concentrations may result in a secondary etch of the aluminum. Low concentrations will not produce a clean aluminum surface, leaving a film that will reduce the quality of your work.
- 5) Small, frequent additions of **ACCU-LABS DX-14 Desmut** will give you more consistent results than larger, less frequent additions. Many factors, such as surface area and drag-out, affect addition rates, and your experience is the best guide to maintenance. The use of an ORP probe and feed pump make solution maintenance simplest.
- 6) Adjust immersion conditions as production changes. There is no combination of time, temperature, and concentration that is suitable to all work.
- 7) **Note: Work processed in DX-14 should not dwell any longer than is necessary to achieve desired surface as this depletes the DX-14 and can adversely affect operating cost. Any work falling into the tank bottom should be retrieved immediately.**

Typical Process Cycle:

- Clean to remove soils and oils with **Accu-Labs 368-G or SR-10**
- Water rinse
- Etch (if necessary) with **Accu-Labs 161 or 366G**
- Water rinse
- Desmut/Deoxidize with **Accu-Labs DX-14**
- Water rinse
- Anodize, Bright Dip, Conversion Coat, Resistance Weld, or Zincate prior to plating.

SOLUTION CONTROL:

- Pipette 10 ml sample of DX-14 bath into a 250 ml Erlenmeyer flask
- Add 50 ml DI water
- Add 2 grams Sodium Gluconate and 5 drops Phenolphthalein indicator
- Titrate with 1.0N sodium hydroxide (NaOH) until a pink color prevails and persists for a minimum of 30 seconds. Record ml of 1.0N NaOH used
- CALCULATION- $1.0 \times \text{ml } 1.0\text{N NaOH} = \% \text{ by volume DX-14}$

Safety and handling

ACCU-LABS DX-14 Desmut is a hazardous product which contains mineral acids, oxidizers and fluorides. Read and understand the Material Safety Data Sheet before using this product. Wear eye and face protection and chemical-resistant protective clothing while handling and working with this material. Store DX-14 in sealed containers in a cool, dry area away from alkaline. DO NOT FREEZE!

Non-warranty

The information contained in this bulletin is, to the best of our knowledge, true and accurate. All recommendations are made without guarantee. Accu-Labs Inc. disclaims any and all liability arising from the use of this product or the information contained herein.