

ACCU-LABS INC.

4831 S. Whipple Avenue
Chicago IL 60632
Phone: 773.523.3100 Fax: 773.523.4008
www.accu-labs.com

A2LA Accredited ISO/IEC 17025:2005 Certificate # 2558.01

PATOX 15

BLACKENING COMPOUND FOR COPPER AND ITS ALLOYS

ACCU-LABS PATOX 15 produces a stable, adherent, and durable black oxide coating on copper and its alloys. The appearance of the finish is dependent upon the condition of the surface. Beautiful glossy black finishes are obtained on buffed or burnished copper and brass. Dull finishes are obtained on sand blasted or etched surfaces. PATOX 15 coatings being stable and absorbent provide a good base for organic finishes such as paints and lacquers.

The coating produced by PATOX 15 is a hard cupric oxide, which is extremely chemically and physically stable, and can withstand severe handling deformations and wear. PATOX 15 coatings withstand temperatures up to 400°F, without breaking down.

Copper alloys of 90% or more present no problems in blackening. Alloys containing less than 90% copper are more difficult to blacken and require the use of PATOX 15A Activator to insure the attainment of a good uniform deep black.

OPERATING GUIDELINES (Alloys Containing Over 90% Copper)

Concentration	1 ½ lb PATOX 15 per gallon of water
Temperature	210-215°F
Tank	Mild or stainless steel
Time of Immersion	5-10 minutes

- 1. Clean**
- 2. Water Rinse**
- 3. Acid Dip**
- 4. Water Rinse**
- 5. Blacken in PATOX 15**
- 6. Rinse**
- 7. Hot water rinse**
- 8. Dry**

OPERATING GUIDELINES

Alloys Containing 65-90% Copper

Concentration	1 lb PATOX per gallon of water
Temperature	Boiling point
Tank	Mild steel
Time of Immersion	1-3 minutes

- 1. Clean**
- 2. Water rinse**
- 3. Acid dip**
- 4. Rinse in cold running water**
- 5. Activate in PATOX 15A Brass Activator**
- 6. Water rinse**
- 7. Blacken in PATOX 15**
- 8. Water rinse**
- 9. Hot water rinse**
- 10. Dry**

CAUTION: PATOX 15A and PATOX 15 are strong alkalis and strong oxidizing agents. Contact with organic material, reducing agents should be avoided. Neoprene gloves, aprons, and goggles should be worn when handling PATOX 15A and 15.

NOTICE OF NON WARRANTY

The information contained in this sheet is true and accurate to the best of our knowledge, but use and conditions are beyond our control. No guarantee is expressed or implied for the above suggestions or recommendations. ACCU-LABS, INC., will not incur liability in connection with the use of these suggestions or technical data.