

4831 S. Whipple Avenue
Chicago IL 60632
Phone: 773.523.3100 Fax: 773.523.4008
www.accu-labs.com

A2LA Accredited ISO/IEC 17025:2005 Certificate # 2558.01

526CC BURNISHING COMPOUND

INTRODUCTION

Accu-Labs 526CC Burnishing Compound has been developed for burnishing of copper, brass, steel, zinc and aluminum to a smooth lustrous finish. Accu-Labs 526CC Burnishing Compound is a dry, non-dusty, mildly alkaline powder, having a pH of approximately 8.5. Accu-Labs 526CC is completely soluble in water and is completely free rinsing.

COMPOSITION

Accu-Labs 526CC is completely soap free and has a balanced composition of biodegradable surfactants of foam and lubrication necessary for high finishing, free from stain or tarnish.

OPERATING PROCEDURE

CONCENTRATION:

 $\frac{1}{2}$ - 2 oz. /gal. of water.

Accu-Labs 526CC can be used in a conventional operating type oblique barrel or in a horizontal barrel. Parts may be tumbled or tumbled in steel media, depending upon the parts. Burnishing times vary depending upon the condition of the metal and the finish desired.

DISCLAIMER

The information contained on this sheet is true and accurate to the best of our knowledge. Because use and conditions are beyond our control, no guarantee is expressed or implied for the above suggestions and/or recommendation. Accu-Labs, Inc. will not incur any liability in connection with the use of these suggestions and/or technical data.