

Accu-LABS INC.

4831 S. Whipple Avenue
Chicago IL 60632
Phone: 773.523.3100 Fax: 773.523.4008
www.accu-labs.com

A2LA Accredited ISO/IEC 17025:2005 Certificate # 2558.01

392 Mid-Phosphorus Semi-Bright Electroless Nickel Plating System

The 392 System is specifically formulated to produce a semi-bright nickel-phosphorus deposit at a consistent high rate of deposition. The 392 System is recommended for applications requiring a semi-bright functional finish and moderate corrosion resistance. The 392 System is available in non-self regulating and self regulating pH packages.

The 392 System offers the following characteristics:

- Exceptional Stability
- Consistent Rate of Deposition
- High Tolerance to Contaminants
- Low Operating Cost

TYPICAL DEPOSIT PROPERTIES:

Phosphorus Content	7%-9% Typical Weight Percentage
Melting Range	1620-1760° F
Density	8.1 Grams per Cubic Centimeter
Hardness	550 HK100 as plated
Magnetic Properties	Slightly Magnetic
Nitric Acid Test	Fails
Hydrochloric Acid Test	Passes
Neutral Salt Spray	Up to 100 hours to first corrosion

BATH OPERATING DATA:

Solution Make-up Materials Required:

- 392-M (Make-up Only) 15% by volume
- 392-N (Nickel Component) 7% by volume
- DI water to operating volume
- 50% Ammonium Hydroxide Solution for pH control especially for steel substrates
- Liquid Potassium Carbonate for pH control especially for aluminum substrates
- NOTE: For Self Regulating processes the 392-RH will usually maintain sufficient pH. However, since conditions vary within each plating operation, there may be a need to add a small amount of ammonium hydroxide or liquid potassium carbonate to the Self Regulating baths to maintain the desired pH. Contact your Accu-Labs Representative for more information.

Accu-LABS INC.

4831 S. Whipple Avenue
Chicago IL 60632
Phone: 773.523.3100 Fax: 773.523.4008
www.accu-labs.com

A2LA Accredited ISO/IEC 17025:2005 Certificate # 2558.01

Accu-Labs 392 makeup procedure:

- Add DI water to properly cleaned and passivated tank (fill to half volume)
- Add required amount of 392-M
- Add required amount of 392-N
- Fill tank to working volume with DI water
- Mix thoroughly with solution and slight air agitation
- Heat to 190° F
- Analyze nickel content and adjust to 6.0 g/l
- Check pH and adjust to *4.70-5.10

Recommended Operating Parameters:

Component	Range	Optimum
Nickel Metal	5.10-6.30 g/l	6.0 g/l
Hypophosphite	27.0 – 33.0 g/l	30.0 g/l
pH	*4.70-5.10	4.90
Temperature	180-200° F	190° F
Bath Loading Sq Ft/Gal	0.10-1.00	0.50

Note: pH can be adjusted upward with a 50% solution of ammonium hydroxide for steel or liquid potassium carbonate for aluminum. If pH needs to be adjusted downward a solution of 10% sulfuric acid can be used. * For applications requiring additional corrosion protection the pH can be lowered to and maintained at 4.50.

Typical Bath Performance:

- Plating Rate-Typically 1.0 mils/hour with all parameters at optimum (new bath)
- Solution Life (Metal Turnovers)
 - Steel 6-10
 - Aluminum
 - Ammonium Hydroxide pH adjust 5-7
 - Potassium Carbonate pH adjust 7-9
 - With Alkaline Strike prior to plate 6-10
 - Individual applications and practices will affect bath life

Bath Maintenance: To ensure proper operation of the 392 system, the solution chemistry should be maintained using the aforementioned operating parameters. This is accomplished by measuring and monitoring the nickel metal concentration. Upon determination of the nickel metal concentration, additions of both 392-N and 392-R (Non-Self pH Regulating) or 392-RH (Self pH Regulating) are made based on the following replenishment guide for a 100-gallon bath:

Nickel %	Nickel Concentration	Additions 392-N	Additions 392-R	Additions 392-RH
100	6.0 grams per liter	None	None	None
95	5.7 grams per liter	1300 mls	1300 mls	1300 mls
90	5.4 grams per liter	2600 mls	2600 mls	2600 mls
85	5.1 grams per liter	3.9 liters	3.9 liters	3.9 liters
80	4.8 grams per liter	5.2 liters	5.2 liters	5.2 liters
75	4.5 grams per liter	6.5 liters	6.5 liters	6.5 liters

Accu-LABS INC.

4831 S. Whipple Avenue
Chicago IL 60632
Phone: 773.523.3100 Fax: 773.523.4008

www.accu-labs.com

A2LA Accredited ISO/IEC 17025:2005 Certificate # 2558.01

NICKEL METAL DETERMINATION:

Reagents:

- 0.0575M EDTA
- 50% Ammonium Hydroxide
- Murexide Indicator

Procedure:

- Add 10 ml bath sample to 100 ml DI water
- Add 10 ml ammonium hydroxide solution
- Add 0.2 grams murexide indicator
- Titrate with EDTA from pale yellow to purple (violet) end point
- Record number of mls of EDTA titrated

Calculation:

- Mls of 0.0575 EDTA x 0.339 = grams/liter nickel or
- Mls of 0.0575 EDTA x 5.65 = % nickel in bath

Handling Considerations:

When handling Accu-Labs 392 components proper precautions should be observed. Do not take internally and avoid contact to skin and eyes. Wear clean chemical resistant gear, goggles, gloves, apron, footwear, and face shield. Accu-Labs recommends reading the MSDS prior to use.

Notice of Disclaimer:

The recommendations contained within this technical data are made in good faith and are based on our technical background and experience. However, since the conditions of use are beyond our control, this knowledge is given on the express terms and agreement that Accu-Labs, Inc. will not be held liable to any person in contract, tort (including negligence), strict liability, or otherwise any claims, damages, or losses whatsoever. Nothing herein shall be deemed a testimonial to use any product or process in infringement of any existing patent rights and no guarantees, expressed or implied, are made regarding information, product, processes, recommendations, description and safety notations contained herein.